



21ST EDITION

Remington

**The Science and Practice
of Pharmacy**



LIPPINCOTT WILLIAMS & WILKINS
A Wolters Kluwer Company

Philadelphia • Baltimore • New York • London
Buenos Aires • Hong Kong • Sydney • Tokyo

Editor: David B. Troy
Managing Editor: Matthew J. Hauber
Marketing Manager: Marisa A. O'Brien

Lippincott Williams & Wilkins

351 West Camden Street
Baltimore, Maryland 21201-2436 USA

530 Walnut Street
Philadelphia, PA 19106

All rights reserved. This book is protected by copyright. No part of this book may be reproduced in any form or by any means, including photocopying, or utilized by any information storage and retrieval system without written permission from the copyright owner.

The publisher is not responsible (as a matter of product liability, negligence or otherwise) for any injury resulting from any material contained herein. This publication contains information relating to general principles of medical care which should not be construed as specific instructions for individual patients. Manufacturer's product information and package inserts should be reviewed for current information, including contraindications, dosages and precautions.

Printed in the United States of America

Entered according to Act of Congress, in the year 1885 by Joseph P Remington, in the Office of the Librarian of Congress, at Washington DC

Copyright 1889, 1894, 1905, 1907, 1917, by Joseph P Remington

Copyright 1926, 1936, by the Joseph P Remington Estate

Copyright 1948, 1951, by the Philadelphia College of Pharmacy and Science

Copyright 1956, 1960, 1965, 1970, 1975, 1980, 1985, 1990, 1995, by the Philadelphia College of Pharmacy and Science

Copyright 2000, 2006, by the University of the Sciences in Philadelphia

All Rights Reserved
Library of Congress Catalog Card Information is available
ISBN 0-7817-4673-6

The publishers have made every effort to trace the copyright holders for borrowed material. If they have inadvertently overlooked any, they will be pleased to make the necessary arrangements at the first opportunity.

The use of structural formulas from USAN and the USP Dictionary of Drug Names is by permission of The USP Convention. The Convention is not responsible for any inaccuracy contained herein.

Notice—This text is not intended to represent, nor shall it be interpreted to be, the equivalent of or a substitute for the official United States Pharmacopeia (USP) and/or the National Formulary (NF). In the event of any difference or discrepancy between the current official USP or NF standards of strength, quality, purity, packaging and labeling for drugs and representations of them herein, the context and effect of the official compendia shall prevail.

To purchase additional copies of this book call our customer service department at (800) 638-3030 or fax orders to (301) 824-7390. International customers should call (301) 714-2324.




Figure 45-10. Rotary granulator and sifter (courtesy, Vector/Colton).

Solutions of the binding agent are added to the mixed powders with stirring. The powder mass is wetted with the binding solution until the mass has the consistency of damp snow or brown sugar. If the granulation is over-wetted, the granules will be hard, requiring considerable pressure to form the tablets, and the resultant tablets may have a mottled appearance. If the powder mixture is not wetted sufficiently, the resulting granules will be too soft, breaking down during lubrication and causing difficulty during compression.

The wet granulation is forced through a 6- or 8-mesh screen. Small batches can be forced through by hand using a manual screen. For larger quantities, one of several comminuting mills suitable for wet screening can be used. These include the Stokes oscillator, Colton rotary granulator, Fitzpatrick comminuting mill, or Stokes tornado mill. See Figure 45-10. In comminuting mills the granulation is forced through the sieving device by rotating hammers, knives, or oscillating bars. Most high-speed mixers are equipped with a chopper blade that operates independently of the main mixing blades and can replace the wet milling step, i.e., can obviate the need for a separate operation.

For tablet formulations in which continuous production is justified, extruders such as the Reitz extruder have been adapted for the wet-granulation process. The extruder consists of a screw mixer with a chamber where the powder is mixed with the binding agent, and the wet mass gradually is forced through a perforated screen, forming threads of the wet granulation. The granulation then is dried by conventional methods. A semiautomatic, continuous process using the Reitz extruder has been described for the preparation of the antacid tablet Gelusil (Warner-Lambert/Pfizer).

Moist material from the wet milling step traditionally was placed on large sheets of paper on shallow wire trays and placed in drying cabinets with a circulating air current and thermostatic heat control. See Figure 45-11. While tray drying was the most widely used method of drying tablet granulations in the past, fluid-bed drying is now considered the standard. In drying tablet granulation by fluidization, the material is suspended and agitated in a warm air stream while the granulation is maintained in motion. Drying tests comparing the fluidized bed

and a tray dryer for a number of tablet granulations indicated that the former was 15 times faster than the conventional method of tray drying. In addition to the decreased drying time, the fluidization method is claimed to have other advantages such as better control of drying temperatures, decreased handling costs, and the opportunity to blend lubricants and other materials into the dry granulation directly in the fluidized bed. See Figure 45-12.³¹

The application of microwave drying and infrared drying to tablet granulations has been reported as successful for moist granulations tried. These methods readily lend themselves to continuous granulation operations. The study of drying methods for tablet granulations led to the development of the Roove dryer system by Ciba/Novartis pharmacists and engineers. The dryer is similar in appearance to the cone blender except for the heating jacket and vacuum connections. By excluding oxygen and using the lower drying temperatures made possible by drying in a vacuum, opportunities for degradation of the ingredients during the drying cycle are minimized. A greater uniformity of residual moisture content is achieved because of the moving bed, controlled temperature, and controlled time period of the drying cycle. Particle-size distribution can be controlled by varying the speed of rotation and drying temperature as well as by comminuting the granulation to the desired granule size after drying.

In drying granulations it is desirable to maintain a residual amount of moisture in the granulation. This is necessary to maintain the various granulation ingredients, such as gums, in a hydrated state. Also, the residual moisture contributes to the reduction of the static electric charges on the particles. In the selection of any drying process, an effort is made to obtain a uniform moisture content. In addition to the importance of moisture content of the granulation in its handling during the manufacturing steps, the stability of the products containing moisture-sensitive active ingredients may be related to the moisture content of the products.

Previously it was indicated that water-soluble colorants can migrate toward the surface of the granulation during the drying process, resulting in mottled tablets after compression. This is also true for water-soluble drug substances, resulting in tablets unsatisfactory as to content uniformity. Migration can be reduced by drying the granulation slowly at low temperatures or using a granulation in which the major diluent is present in granules of large particle size. The presence of microcrystalline cellulose in wet granulations also reduces migration tendencies.

After drying, the granulation is reduced in particle size by passing it through a smaller-mesh screen. Following dry screening, the granule size tends to be more uniform. For dry granulations the screen size to be selected depends on the diameter of the punch. The following sizes are suggested:

Tablets up to $\frac{1}{8}$ inch diameter, use 20-mesh
Tablets $\frac{1}{8}$ to $\frac{1}{4}$ inch, use 16-mesh
Tablets $\frac{1}{4}$ to $\frac{1}{2}$ inch, use 14-mesh
Tablets $\frac{1}{2}$ inch and larger, use 12-mesh

For small amounts of granulation, hand screens may be used and the material passed through with the aid of a stainless steel spatula. With larger quantities, any of the comminuting mills




Figure 45-11. Cross-section of tray dryer.